



Europäisches Patentamt  
European Patent Office  
Offic européen des brevets

(11) EP 0 999 242 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:  
10.05.2000 Bulletin 2000/19

(51) Int. C09D 5/24, C08G 61/12  
Cl.7:

(21) Application number: 99121646.6

(22) Date of filing: 01.11.1999

(84) Designated Contracting States:  
AT BE CH CY DE DK ES FI FR GB GR IE IT  
LI LU MC NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI

(30) Priority: 05.11.1998 KR 9847281

(71) Applicant: Samsung General Chemicals  
Co., Ltd.  
Seosan-shi, Chungcheongnam-do 352-  
870 (KR)

(72) Inventors:  
, Kim, Hyun Don  
Yousung-gu, Taejon-shi, 352-870 (KR)  
, Chung, Hae Ryong  
Suwon-shi, Kyungki-do, 440-300 (KR)  
, Cheong, Min Kyo

Seoul, 122-130 (KR)  
, Chang, Tu Won  
Yousung-gu, Taejon-shi, 305-390 (KR)

(74) Representative:  
Troesch Scheidegger Werner AG  
Patentanwälte,  
Siewerdtstrasse 95,  
Postfach  
8050 Zürich (CH)

Remarks:  
A request for correction of the  
description has been filed pursuant to  
Rule 88 EPC. A decision on the request  
will be taken during the proceedings  
before the Examining Division  
(Guidelines for Examination in the EPO,  
A-V, 3.).

(54) Polythiophene-based conductive polymer liquid composition of high conductivity and transparency

(57) Disclosed are polythiophene-based conductive polymer liquid compositions of high conductivity and transparency. The compositions comprise 16-32 weight % of an aqueous polythiophene-based conductive polymer solution, 52-80 weight % of an alcohol solvent, 1-12 weight % of an amide solvent, 0.01-0.4 weight % of a sulfonic acid group-containing monomer dopant, and optionally 2-8 weight % of an

alkoxysilane. The compositions can be applied to transparent substrates to form coatings which have a surface resistance of 1 kΩ/□ or less and a transmittance of 92 % or higher. With the excellent conductivity and transparency, the compositions are useful as electromagnetic wave-shielding materials, finding numerous applications in cathode ray tube screens (TV sets and computer monitors) as well as CPP films, polyethyleneterephthalate films, polycarbonate panels, and acryl panels.

## Description

## BACKGROUND OF THE INVENTION

## 1. Description of the invention

The present invention relates to a polythiophene-based polymer liquid composition, which can be formed into a coating with high conductivity and high transparency. More particularly, the present invention is concerned with the use of an amide solvent and a sulfonic acid group ( $\text{SO}_3\text{H}$ )-containing monomer dopant in improving the conductivity and transparency of a polythiophene-based polymer liquid composition.

## 2. Description of the Prior Art

Polyethylenedioxythiophene (PEDT), a conductive polymer, was disclosed as an antistatic property-imparting material, such as an antistatic coating, in U.S. Pat. Nos. 5,035,926 and 5,391,472. Since then, intensive attention has been paid to polymer-based conductive coatings applicable to glass surfaces of Braun tubes.

In terms of electrical conductivity, this conductive polymer has advantages over well-known preexisting polymers, such as polyanilines, polypyrroles and polythiophenes. PEDT also shows excellent processability by virtue of its ability to be easily formed into a coating solution which is dispersible in water, along with salts of polymer acids (e.g., polystyrene sulfonate) as dopants. With this good water dispersibility, PEDT can be well dissolved in alcohol solvents, and the aqueous dispersions find numerous applications in Braun tube (CRT) glasses, plastic film surfaces, etc. The use of water and alcohols as solvents is ecologically very favorable.

Such water-dispersible PEDT polymers are now commercially available, representatively exemplified by Baytron P (Grade A4071) from Bayer.

Highly transparent as they are, conductive PEDT polymers must be coated at low PEDT contents (24 % or less based on 1.3 wt% solution) in order to exhibit a transmittance of 92 %. Accordingly, it is difficult to achieve a surface resistance of 100  $\text{k}\Omega$  or less through ordinary techniques. In order to reinforce the strength of PEDT coatings, there is used silica sols prepared from alkoxy silane (e.g., alkyltriethoxysilane), represented by  $\text{RSi}(\text{OR})_3$  wherein R is methyl, ethyl, propyl or isobutyl and R is methyl or ethyl. In this case, the conductivity of the resulting coatings is aggravated owing to silica sol. Thus, it is more impossible for existing techniques to produce conductive coatings with a surface resistance of 100  $\text{k}\Omega/\%$  or less. In fact, current techniques can use PEDT as an antistatic coating material only where low conductivity is required (see technical reference for Baytron P, Bayer).

Therefore, it is virtually impossible for currently prevailing techniques to achieve a transmittance of 92 % in addition to a surface resistance of 1  $\text{k}\Omega/\%$  or less, which satisfies TCO (Tianstemanners Central Organization) Standards for commercially competitive electromagnetic wave-shielding materials.

## SUMMARY OF THE INVENTION

Therefore, it is an object of the present invention to overcome the problems encountered in

## EP 0 999 242 A1

prior arts and to provide a highly conductive and transparent polythiophene-based composition with which a coating having a surface resistance of  $1 \text{ k}\Omega/\square$  or less and a transmittance of 92 % can be formed on a transparent substrate.

5 It is another object of the present invention to provide polythiophene-based compositions useful as electromagnetic wave-shielding materials which are applicable for Braun tube surfaces.

10 Leading to the present invention, the intensive and thorough research on the development of polythiophene-based compositions of high conductivity and transparency, repeated by the present inventor aiming to satisfy the TCO Standards in surface resistance, resulted in the finding that PEDT conductive polymer solutions can be greatly improved in electrical conductivity by the presence of amide-based organic solvents or sulfonic acid-containing  
15 monomer dopants, and even more improved by adding the solvents and the dopants in combination than alone.

### DETAILED DESCRIPTION OF THE PRESENT INVENTION

20

In accordance with a first embodiment of the present invention, there is provided a polythiophene-based polymer liquid composition of high conductivity and transparency comprising 16-32 weight % of an aqueous polythiophene-based conductive polymer solution,  
25 56-82 weight % of an alcohol containing 1-4 carbon atoms, 1-12 weight % of an amide solvent, and 0.01-0.2 weight % of a monomer dopant containing a sulfonic acid group, characterized in that it provides a coating which is  $1 \text{ k}\Omega/\square$  or less in surface resistance, 92 % or greater in transmittance, and B or smaller in pencil hardness. The composition of the present invention  
30 may be coated on transparent substrates which are used where large hardness is not required. If large hardness is necessary, a silica sol solution may be further applied on the coating of the present invention.

35 When being coated on transparent substrates, such as glass and synthetic plastic films, the composition of the present invention promises to show a surface resistance of  $1 \text{ k}\Omega/\square$ , a transmittance of 90-98 %, and a hardness of 2-9 H.

The conductive polymer useful in the present invention is PEDT, such as that commercially available from Bayer, identified as "Baytron P". Because of being doped with polystyrene  
40 sulfonate (PSS), the PEDT polymer is well dissolved in water in addition to exhibiting excellent thermal stability and atmospheric stability. Further, the aqueous polythiophene-based conductive polymer solution was found to maintain optimal water dispersibility when comprising PEDT and PSS at a total solid content of 1.0-1.5 weight %. High solubility in water, alcohol, and  
45 solvents of large dielectric constants makes it easy to prepare a coating solution of high coatability. Furthermore, the coatings have a great advantage over those of other conductive polymers, such as polyaniline and polypyrrole, in terms of transparency.


50 In the polythiophene-based composition, the conductive PEDT polymer is preferably used at an amount of 16-32 weight %. For example, if too little PEDT polymer is used, desired high conductivity, such as a surface resistance of as low as  $1 \text{ k}\Omega/\square$ , cannot be achieved no matter how much the amide solvent and the sulfonic acid monomer dopant may be used. On the other  
55 hand, an amount greater than 32 weight % causes the resulting coatings to be lower in transmittance than 92 % because light is shielded by the characteristic color that the PEDT itself retains.

# EP 0 999 242 A1

Serving as a solvent for the conductive PEDT polymer, an alcohol is contained in the composition of the present invention. Useful are alcohols containing 1-4 carbon atoms, exemplified by methanol, ethanol, propanol, isopropanol and butanol. These alcohol solvents may be used alone or in combination. Most preferable is a mixture of two or three alcohols which are different from each other in boiling point. While being vaporized in sequence, the mixed alcohols assure the coating of a highly dispersed state of the PEDT conductive polymer.

Such an alcohol solvent is preferably used at an amount of 56-82 weight %. For example, when the alcohol solvent is used at an amount of less than 16 weight %, the coating is poor in dispersibility. On the other hand, an alcohol amount exceeding 82 weight % brings about a good result in dispersibility, but causes a significant problem in conductivity.

As for the amide solvent useful in the present invention, it is represented by the following formula:



wherein,  $R^1\text{a}$ ,  $R^2\text{a}$  and  $R^3\text{a}$ , which may be the same or different, each denotes H,  $\text{CH}_3$  or  $-\text{CH}_2\text{CH}_2\text{CH}_2-$ . Examples of the amide solvents include formamide (FA), N-methylformamide (NMFA), N,N-dimethylformamide (DMF), acetamide (AA), N-methylacetamide (NMAA), N,N-dimethylacetic amide (DMA), N-methylpropion amide (NMPA) and N-methylpyrrolidone.

As well as serve as a solvent in the polythiophene-based polymer solution, the amide compounds, alone or in combination, play a role in increasing conductivity. The increasing effects on conductivity are grouped according to the kinds of amide solvents in Table 1, below.

TABLE 1

Effect of Amide Solvents on Conductivity				
	Group 1	Group 2	Group 3	Group 4
Improving Effect On Conductivity	Very Good	Good	Moderate	Small
Amide Solvents		FA		
		NMP		
		NMAA	NMFA	
	FA+NMP	NMPA	NMP+DMP	DMF
	FA+NMAA	NMAA+NMP	NMAA+DMF	DMA
		NMPA+NMP	NMPA+DMF	DMF+NMFA
		NMPA+NMAA	FA+DMF	DMA+NMFA
		FA+NMPA		
		FA+NMPA		

Generally, as seen in Table 1, better results can be obtained when using such amide solvents, in mixture than when alone. Only the amide solvents can assure a transmittance of 92 %, but cannot reduce the surface resistance down to 3  $\text{k}\Omega/\square$ , however much they may improve

## EP 0 999 242 A1

the conductivity. This is very insufficient for the goal that the present invention intends to achieve. In the present invention, as will be described later, the amide solvents are used in combination with sulfonic acid group-containing monomer dopants, so as to accomplish the desired conductivity, such as a surface resistance of 1 k $\Omega$ /%, and the desired transparency, such as a transmittance of 92 % or higher. To this end, preferable is Group 1 or 2 of Table 1.

Preferably, the amide solvent is used at an amount of 1-12 weight %. For instance, if present at an amount of less than 1 weight %, the amide solvent cannot allow the surface resistance to be reduced down to 1 k $\Omega$ /%, even when increasing the amount of the additionally added dopant. On the other hand, too much amide solvent deleteriously affects the solubility of the dopant, thereby improving the conductivity no more. In addition, because of their high boiling points, the amide solvents, when added at large amounts, force the coatings to be dried at high temperatures, deteriorating the conductivity of the PEDT conductive polymer.

In accordance with the present invention, the PEDT conductive polymer is further doped with monomer dopants containing sulfonic acid groups. Examples of the monomer dopants include p-toluene sulfonic acid (p-TSA), dodecylbenzene sulfonic acid (DOBSA), 1,5-anthraquinonedisulfonic acid (1,5-AQSA), anthraquinonesulfonic acid (AQSA), 4-hydroxybenzene sulfonic acid (4-HBSA), methylsulfonic acid (MSA) and nitrobenzene sulfonic acid (NBSA). In the case that the monomer dopants exist as salts, such as sodium salts, they can be converted to acid forms using a nitric acid solution (pH 2). For use, the dopants in an acid form are made into an aqueous solution which has a concentration of 1-4 weight % and preferably 1-2 weight %. When being added with their phase in an aqueous solution form, the monomer dopants are more uniformly dispersed throughout the conductive polymer, so as to bring about better results in conductivity and coating uniformity, than when being added with their phase in a solid form (or crude liquid form). The dopants stabilize charges in the PEDT conductive polymers, giving a great contribution to the conductivity of the polymers. Advantageous in the aspect of conductivity are dopants which are small in molecular size, like p-TSA, 4-HBSA and NBSA. The dopants are preferably used at an amount of 0.01-0.2 weight % based on the weight of the composition. For instance, when the dopants are added at an amount of more than 0.2 weight %, the dopants make coatings rather decrease than increase in conductivity while being poorly dispersed in the coatings. On the other hand, when too little dopants are used, it is virtually impossible to approach the desired conductivity, that is, a surface resistance of 1 k $\Omega$ /%.

The polythiophene-based, conductive polymer composition of high conductivity and transparency may be prepared by adding a PEDT conductive polymer with a sulfonic acid monomer dopant, an alcohol solvent and an amide solvent, in due order, at intervals of 1 min with vigorous stirring, and mixing them homogeneously for 2-4 hours.

From this polythiophene-based, conductive polymer composition, there can be formed highly transparent and conductive coatings which are capable of shielding electromagnetic waves. For this, first, the polythiophene-based, conductive polymer compositions according to the present invention are poured on transparent substrates, such as cathode ray tube screens (TV sets and computer monitors), CPP (casting polypropylene) films, polyethyleneterephthalate films, polycarbonate panels, and acryl panels, and uniformly spread by a bar coating or spin coating manner, followed by drying at 80-140°C for 10-30 min in an oven. As a result, there are obtained polythiophene coatings of high conductivity which are of low hardness and useful for shielding electromagnetic waves.

In accordance with a second embodiment of the present invention, there is provided a

## EP 0 999 242 A1

polythiophene-based polymer liquid composition of high conductivity and transparency comprising 16-32 weight % of an aqueous polythiophene-based conductive polymer solution, 2-8 weight % of an alkoxy silane, 52-80 weight % of an alcohol containing 1-4 carbon atoms, 1-8 weight % of an amide solvent, and 0.01-0.4 weight % of a monomer dopant containing a sulfonic acid group, characterized in that it provides a coating which is 1 k $\Omega$ /sq or less in surface resistance, 92 % or greater in transmittance, and 2H or greater in pencil hardness. The composition of the present invention may be coated on transparent substrates which are used where large hardness is required. If larger hardness is necessary, a 100% silica sol solution may be further applied on the coating of the present invention to allow the coating to have a hardness of as high as 9H.

The conductive polymer useful in this embodiment is PEDT, such as that commercially available from Bayer, identified as "Baytron P". By virtue of being doped with polystyrene sulfonate (PSS), the PEDT polymer is well dissolved in water in addition to exhibiting excellent thermal stability and atmospheric stability. Further, the aqueous polythiophene-based conductive polymer solution can maintain optimal water dispersibility when comprising PEDT and PSS at a total solid content of 1.0-1.5 weight %. Its high solubility in water, alcohol, and solvents of large dielectric constants makes it easy to prepare a coating solution of high coatability. Furthermore, the coatings have a great advantage over those of other conductive polymers, such as polyaniline and polypyrrole, in terms of transparency.

In the polythiophene-based composition, the conductive PEDT polymer is preferably used at an amount of 16-32 weight %. For example, if too little PEDT polymer is used, desired high conductivity, such as a surface resistance of as low as 1 k $\Omega$ /sq, cannot be achieved no matter how much the amide solvent and the sulfonic acid monomer dopant may be used. On the other hand, an amount greater than 32 weight % causes the resulting coatings to be lower in transmittance than 92 % because light is shielded by the characteristic color that the PEDT itself retains.

Serving as a solvent for the conductive PEDT polymer, an alcohol is contained in the composition according to the present invention. Useful are alcohols containing 1-4 carbon atoms, exemplified by methanol, ethanol, propanol, isopropanol and butanol. These alcohol solvents may be used alone or in combination. Most preferable is a mixture of two or three alcohols which are different from each other in boiling point. While being vaporized in sequence, the mixed alcohols assure the coating of a highly dispersed state of the PEDT conductive polymer.

Such an alcohol solvent is preferably used at an amount of 52-80 weight %. For example, when the alcohol solvent is used at an amount of less than 16 weight %, the coating is poor in dispersibility. On the other hand, an alcohol amount exceeding 80 weight % brings about a good result in dispersibility, but causes a significant problem in conductivity.

Being formed into silica sol in the present invention, the alkoxy silane is preferably selected from alkyltrialkoxysilane ( $\text{RSi}(\text{OR}')_3$ , wherein R' is methyl or ethyl and R is methyl, ethyl, or propyl) and tetraalkoxysilane ( $\text{Si}(\text{OR}')_4$ , wherein R' is methyl or ethyl). Preferable amounts of the alkoxy silane are within the range of 2-8 weight %. For example, an amount less than 2 weight % does not assure a hardness of 2H. On the other hand, when too much alkoxy silane is used, the coating has high hardness, but poor conductivity. In this case, the composition is relatively rich in silica sol and the coating obtained after the composition is coated and thermally cured, and is also rich in non-conductive polysilicate as a result of the

## EP 0 999 242 A1

condensation of the silica sol. In addition, too much alkoxy silane is problematic in the aspect of dispersion.

As for the amide solvent useful in the present invention, it is represented by the following formula:



wherein,  $R^1\text{a}$ ,  $R^2\text{a}$  and  $R^3\text{a}$ , which may be the same or different, each denotes H,  $\text{CH}_3$  or  $-\text{CH}_2\text{CH}_2\text{CH}_2-$ . Examples of the amide solvents include formamide (FA), N-methylformamide (NMFA), N,N-dimethylformamide (DMF), acetic acid (AA), N-methylacetamide (NMAA), N,N-dimethylacetamide (DMA), N-methylpropion amide (NMPA) and N-methylpyrrolidone.

In addition to serving as a solvent in the polythiophene-based polymer solution, the amide compounds, alone or in combination, play a role in increasing conductivity. The increasing effects on conductivity are grouped according to the kinds of amide solvents in Table 1. Generally, as seen in Table 1, better results can be obtained when using such amide solvents in mixture than when alone. Only the amide solvents can assure a transmittance of 92 %, but cannot reduce the surface resistance down to 3  $\text{k}\Omega/\%$  no matter how much they may improve the conductivity. This is very insufficient for the goal that the present invention intends to achieve. In the present invention, as will be described later, the amide solvents are used in combination with sulfonic acid group-containing monomer dopants, so as to accomplish the desired conductivity, such as a surface resistance of 1  $\text{k}\Omega/\%$ , and the desired transparency, such as a transmittance of 92 % or higher. To this end, preferable is Group 1 or 2 of Table 1.

Preferably, the amide solvent is used at an amount of 1-8 weight %. For instance, too much amide solvent deleteriously affects the solubility of the dopant so that a desired conductivity cannot be accomplished. In addition, because of their high boiling points, the amide solvents, when added at large amounts, force the coatings to be dried at high temperatures, deteriorating the conductivity of the PEDT conductive polymer. On the other hand, if present at an amount of less than 1 weight %, the amide solvent cannot allow the surface resistance to be reduced down to 1  $\text{k}\Omega/\%$ .

In accordance with the present invention, the PEDT conductive polymer is further doped with monomer dopants containing sulfonic acid groups. Examples of the monomer dopants include p-toluene sulfonic acid (p-TSA), dodecylbenzene sulfonic acid (DOBSA), 1,5-anthraquinonedisulfonic acid (1,5-AQSA), anthraquinonesulfonic acid (AQSA), 4-hydroxybenzene sulfonic acid (4-HBSA), methylsulfonic acid (MSA) and nitrobenzene sulfonic acid (NBSA). Preferable amounts of the dopants are within the range of 0.01-0.4 weight %. For instance, when the dopants are added at an amount of more than 0.4 weight %, the dopants make coatings decrease rather than increase in conductivity while being poorly dispersed in the coatings. On the other hand, when the amount of the dopants are below 0.1 weight %, it is virtually impossible to approach the desired conductivity, that is, a surface resistance of 1  $\text{k}\Omega/\%$ . In the case that the monomer dopants exist as salts, such as sodium salts, they can be converted to acid forms using a nitric acid solution (pH 2). For use, the dopants in an acid form are made into an aqueous solution which has a concentration of 1-4 weight % and preferably 1-2 weight %. When being added with their phase in an aqueous solution form, the monomer dopants are more uniformly dispersed throughout the conductive polymer, so as to bring about better results in conductivity and coating uniformity, than when being added with their phase in a solid form

## EP 0 999 242 A1

(or crude liquid form). The dopants stabilize charges in the PEDT conductive polymers, giving a great contribution to the conductivity of the polymers. Advantageous in the aspect of conductivity are dopants which are small in molecular size, like p-TSA, 4-HBSA and NBSA.

5 The composition of the present invention may be prepared in two mixing processes: two-step mixing process (Process 1) and direct mixing process (Process 2). The two-step mixing process (Process 1) comprises a first step of preparing a silica sol solution and a second step of preparing a silica sol-PEDT mixture solution. In the first step, the silica sol solution is  
10 prepared by mixing alkoxysilane, an alcohol solvent and water for 8-12 hours at room temperature. The mixing of the silica sol solution with a PEDT solution (for example, 1.3 weight %), a sulfonic acid group-containing monomer dopant solution, and an amide solvent for 4-6 hours at room temperature produces a PEDT solution of high hardness and conductivity, leading  
15 to the second step.

As for the direct mixing process (Process 2), it comprises mixing a PEDT solution (for example, 1.3 weight %), alkoxysilane, an alcohol solvent, an amide solvent and a sulfonic acid group-containing monomer dopant solution all together for 6-10 hours to give a PEDT solution of  
20 high hardness and conductivity.

Either of these two mixing processes (Process 1 and Process 2) may be employed to prepare the polythiophene-based conductive polymer liquid composition of high conductivity and transparency according to the present invention with preference to Process 2 (the direct mixing  
25 process) in an aspect of hardness.

From this polythiophene-based, conductive polymer liquid composition, there can be formed highly transparent, hard and conductive coatings which are capable of shielding electromagnetic waves. For this, first, the polythiophene-based, conductive polymer compositions according to  
30 the second embodiment of the present invention are poured on transparent substrates, such as cathode ray tube screens (TV sets and computer monitors), and uniformly spread by a bar coating or spin coating manner, followed by drying at 150-180°C for 0.5-1 hour in an oven. As a result, there are obtained polythiophene coatings of high conductivity which are of high  
35 hardness and useful for shielding electromagnetic waves.

A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present  
40 invention.

### EXAMPLES I TO XIV AND COMPARATIVE EXAMPLES I TO V

45 Polythiophene-based conductive polymer liquid compositions which could be used to form coatings of high transparency and conductivity and low hardness, according to the present invention, were prepared as indicated in Table 2, below. For comparison, only one amide solvent was used, only one sulfonic acid monomer was used, or amounts of components were not in the range suggested in the invention.

50 The aqueous conductive polymer solution used in these examples was Baytron P (Grade A4071) (solid content 1.3 wt%) of Bayer. For the methanol and ethanol, the products purchased from Aldrich were used without modification. The sulfonic acid monomer dopants, P-TSA, 1,5-AQSA, 2,6-AQSA, 4-HBSA and NBSA, which were used to dope the polymer, were in a salt form  
55 when being purchased from Aldrich. For use, they were dissolved in water to give 1 wt% solutions and then converted to acid forms by use of a nitric acid solution (pH 2). Indicated in



# EP 0 999 242 A1

Table 2 were the amounts of aqueous 1 wt% solutions of the monomer dopants.

Aqueous PEDT conductive polymer solutions (PEDT(aq)) were added with sulfonic acid monomer dopant solutions, alcohol, and amide solutions in sequence with vigorous stirring. After completion of the addition, the solutions were further stirred for about 2 hours to give coating solutions. These solutions were spin-coated on glass surfaces, which had been washed with acid and dried, and subjected to drying at 120 °C for 30 min in an oven to form coatings 0.5 μ or less thick.

The coatings were measured for physical properties and the results are given in Table 2. In this regard, an ohm meter was used for surface resistance. The transparency of the coatings was evaluated by measuring their transmittance at 550 nm with a UV-visible meter. Pencil hardness was introduced to represent the hardness of the coatings.

TABLE 2

Ex. Nos.	PEDT/Alcohol/Amide/Dopant (wt%)	Physical Properties of Coating			
		Surface Resist. (kΩ/□)	Transmittance (T%)	Hardness (H)	Uniformity
1	PEDT(aq)/MeOH/FA/NMP/p-TSA (20/72/2/1/5)	0.9	97	≤B	Good
2	PEDT(aq)/MeOH/FA/NMP/p-TSA (24/68/2/1/5)	0.9	95	≤B	Good
3	PEDT(aq)/MeOH/FA/NMP/p-TSA (30/62/2/1/5)	0.65	93	≤B	Good
4	PEDT(aq)/MeOH/FA/NMP/1, 5-AQSA (24/68/2/1/5)	0.85	94	≤B	Good
5	PEDT(aq)/MeOH/FA/NMP/2, 6-AQSA (24/68/2/1/5)	0.90	94	≤B	Good
6	PEDT(aq)/MeOH/FA/NMP/4-HBSA (24/68/2/1/5)	0.75	94	≤B	Good
7	PEDT(aq)/MeOH/FA/NMP/NBSA (24/68/2/1/5)	0.80	94	≤B	Good
8	PEDT(aq)/MeOH/FA/NMAA/p-TSA (24/68/2/1/5)	0.65	94	≤B	Good

**EP 0 999 242 A1**

Ex. Nos.	PEDT/Alcohol/Amide/Dopant (wt%)	Physical Properties of Coating			
		Surface Resist. (k $\Omega$ /sq.)	Transmittance (T%)	Hardness (H)	Uniformity
9	PEDT(aq)/EtOH/FA/NMP/4-HBSA (24/68/2/1/5)	0.75	94	≤B	Good
10	PEDT(aq)/MeOH/FA/NMP/4-HBSA (24/65/4/2/5)	0.70	95	≤B	Good
11	PEDT(aq)/MeOH/FA/NMP/4-HBSA (24/60/4/2/10)	0.75	93	≤B	Very Good
12	PEDT(aq)/MeOH/NMP/4-HBSA (24/64/4/3/5)	0.50	93	B	Good
13	PEDT(aq)/MeOH/NMP/4-HBSA (24/68/2/1/5)	0.85	94	B	Good
14	PEDT(aq)/MeOH/NMP/4-HBSA (24/68/2/1/5)	0.88	94	B	Good
1	PEDT(aq)/MeOH/FA/NMP (24/73/2/1)	4	95	B	Good
2	PEDT(aq)/MeOH/p-TSA (24/71/5)	20	92	B	Good
3	PEDT(aq)/MeOH/NMP/4-HBSA (36/56/2/1/5)	0.5	90	B	Good
4	PEDT(aq)/MeOH/NMP/4-HBSA (24/57/7/7/5)	0.8	95	B	Poor (whitening)
5	PEDT(aq)/MeOH/NMP/4-HBSA (24/43/1/2/30)	2	92	B	Poor (black spot)

As apparent from the data of Table 2, the compositions deviated from the scope of the present invention were found to be poor in all of conductivity, transmittance and dispersibility.

It should be noted that the compositions suggested in Table 2 are set forth to illustrate the

# EP 0 999 242 A1

invention, but do not limit the scope of the present invention.

## EXAMPLES XV TO XXXI AND COMPARATIVE EXAMPLES VI TO XII

5

Polythiophene-based conductive polymer liquid compositions which could be used to form coatings of high transparency and conductivity and hardness, according to the present invention, were prepared as indicated in Table 3, below. For comparison, only one amide solvent was used, only one sulfonic acid monomer was used, or amounts of components were not in the range suggested in the invention. The aqueous conductive polymer solutions, alcohol solvents, amide solvents, sulfonic acid monomer dopants used in these examples were the same as those of Table 2. For alkoxysilane, tetraethoxysilane (TEOS) and MTEOS were used without modification of the products of Aldrich.

For the coatings of Examples XV to XVII, the solutions which were prepared through the direct mixing process (Process 2) were used. The solutions were mixed for about 8 hours at room temperature. The solutions for the coatings of Examples XVIII to XXXI were prepared by the two-step mixing process (Process 1). The mixing for the silica sol solution (step 1) and the silica sol-PEDT conductive polymer solution (step 2) were carried out for 10 hours and 5 hours, respectively.

The preparation of coatings and the measurement of their physical properties followed the procedures of Example I. The results are given in Table 3, below.

TABLE 3

Ex. Nos.	PEDT/Alcohol/Amide/Dopant (wt%)	Physical Properties of Coatings			
		Surface Resist. (K $\Omega$ /sq)	Transmittance (T%)	Hardness (H)	UniFormity
15	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (20/4/63/2/1/10)	0.95K	97	9	Good
16	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (24/4/59/2/1/10)	0.80K	95	7	Good
17	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (30/4/53/2/1/10)	0.78K	92	7	Good
18	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (20/4/63/2/1/10)	0.98K	96	6	Good
19	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (24/4/59/2/1/10)	0.85K	95	4	Good
20	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (30/4/53/2/1/10)	0.83K	92	2	Good

**EP 0 999 242 A1**

Ex. Nos.	PEDT/Alcohol/Amide/Dopant (wt%)	Physical Properties of Coatings			
		Surface Resist. (K $\Omega$ /%)	Transmittance (T%)	Hardness (H)	UniFormity
21	PEDT(aq) /TEOS/MeOH/FA/NMP/1.5- AQSA (26/4/57/2/1/10)	0.83K	95	4	Good
22	PEDT(aq) /TEOS/MeOH/FA/NMP/2.6- AQSA (26/4/57/2/1/10)	0.85K	95	4	Good
23	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (26/4/57/2/1/10)	0.82K	95	4	Good
24	PEDT(aq) /TEOS/MeOH/FA/NMP/NBSA (26/4/57/2/1/10)	0.83K	95	4	Good
25	PEDT(aq) /TEOS/MeOH/FA/NMAA/p-TSA (26/4/57/2/1/10)	0.80K	95	4	Good
26	PEDT(aq) /TEOS/EtOH/FA/NMP/4-HBSA (26/4/57/2/1/10)	0.82K	94	4	Good
27	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (26/4/54/2/10)	0.80	96	4	Good
28	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (26/4/59/4/2/5)	0.82	94	4	Very good
29	PEDT(aq) /TEOS/MeOH/NMAA/NMP/4 HBSA(26/4/57/2/1/10)	0.90	94	4	Good
30	PEDT(aq) /TEOS/MeOH/NMPA/NMAA/4- HBSA (26/4/57/2/1/10)	0.90	94	4	Good
31	PEDT(aq) MTEOS/TEOS/MeOH/FA/NMP/ 4HBSA (26/1/3/57/2/1/10)	0.85	94	3	Good

EP 0 999 242 A1

Ex. Nos.	PEDT/Alcohol/Amide/Dopant (wt%)	Physical Properties of Coatings			
		Surface Resist. (K $\Omega$ /sq)	Transmittance (T%)	Hardness (H)	UniFormity
6	PEDT(aq) TEOS/MeOH/FA/NMP (26/4/77/2/1)	6K	95	B	Good
7	PEDT(aq)/TEOS/MeOH/p-TSA (26/4/60/10)	10K	92	B	Good
8	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (36/4/57/2/1/10)	1K	90	B	Good
9	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (26/6/52/6/10)	0.9K	95	B	Poor (whitening)
10	PEDT(aq) /TEOS/MeOH/FA/NMP/4-HBSA (26/4/22/1/2/45)	0.95K	92	B	Poor (black spot)
11	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (26/1/60/1/2/10)	0.78	95	1	Good
12	PEDT(aq) /TEOS/MeOH/FA/NMP/p-TSA (26/10/58/1/2/10)	6K	94	6	Poor

As described hereinbefore, the polythiophene-based, conductive polymer liquid compositions of the present invention can be applied to transparent substrates, such as glass and synthetic plastic films, to form coatings which have a surface resistance of 1 k $\Omega$ /sq or less, meeting the TCO standards, established by the Laborer Association of Sweden, which are the strictest regulations in the world concerning the shielding of electromagnetic waves. When using alkoxysilane, the coatings thus obtained range, in surface resistance, from 0.54 to 1 k $\Omega$ /sq, in transmittance from 92 to 97 %, and, in pencil hardness from 2 to 9 H. With the high conductivity, transparency and hardness, the polythiophene-based conductive polymer liquid compositions of the present invention are therefore useful as electromagnetic wave-shielding materials. The compositions find numerous applications in cathode ray tube screens (TV sets and computer monitors) as well as CPP films, polyethyleneterephthalate films, polycarbonate panels, and acryl panels.

The present invention has been described in an illustrative manner, and it is to be understood that the terminology used is intended to be in the nature of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. Therefore, it is to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

Claims

- 5       1. A polythiophene-based conductive polymer liquid composition of high conductivity and transparency, comprising:
- 16-32 weight % of an aqueous polythiophene-based conductive polymer solution;
- 10       56-82 weight % of an alcohol solvent;
- 1-12 weight % of an amide solvent; and
- 15       0.01-0.2 weight % of a sulfonic acid group-containing monomer dopant.
- 20       2. A polythiophene-based conductive polymer liquid composition as set forth in claim 1, wherein the aqueous conductive polymer solution is an aqueous polyethylenedioxythiophene solution.
- 25       3. A polythiophene-based conductive polymer liquid composition as set forth in claim 1, wherein the aqueous conductive polymer solution has a solid content of 1.0-1.5 weight %.
- 30       4. A polythiophene-based conductive polymer liquid composition as set forth in claim 1, wherein the alcohol contains 1-4 carbon atoms.
- 35       5. A polythiophene-based conductive polymer liquid composition as set forth in claim 1, wherein the amide solvent is selected from the group consisting of formamide, N-methylformamide, N,N-dimethylformamide, acetamide, N-methylacetamide, N,N-dimethylacetic amide, N-methylpropion amide, N-methylpyrrolidone, and mixtures thereof.
- 40       6. A polythiophene-based conductive polymer liquid composition as set forth in claim 1, wherein the sulfonic acid group-containing monomer dopant is selected from the group consisting of p-toluene sulfonic acid, dodecylbenzene sulfonic acid, 1,5-anthraquinonedisulfonic acid, anthraquinonesulfonic acid, 4-hydroxybenzene sulfonic acid, methylsulfonic acid and nitrobenzene sulfonic acid.
- 45       7. A polythiophene-based conductive polymer liquid composition of high conductivity and transparency, comprising:
- 50       16-32 weight % of an aqueous polythiophene-based conductive polymer solution;
- 2-8 weight % of an alkoxysilane;
- 55       52-80 weight % of an alcohol solvent;
- 1-8 weight % of an amide solvent; and

EP 0 999 242 A1

0.01-0.4 weight % of a sulfonic acid group-containing monomer dopant.

5

8. A polythiophene-based conductive polymer liquid composition set forth in claim 7, wherein the aqueous polythiophene-based conductive polymer solution is an aqueous polyethylenedioxythiophene solution.

10

9. A polythiophene-based conductive polymer liquid composition as set forth in claim 7, wherein the aqueous conductive polymer solution has a solid content of 1.0-1.5 weight %.

15

10. A polythiophene-based conductive polymer liquid composition as set forth in claim 7, wherein the alkoxysilane is a tetraalkoxysilane or alkyltrialkoxysilane, represented by the following chemical formulas 1 and 2, respectively:

20



25



wherein, R is methyl, ethyl, propyl or isobutyl;  $\text{R}^1$  is methyl or ethyl.

30

11. A polythiophene-based conductive polymer liquid composition as set forth in claim 7, wherein the alcohol contains 1-4 carbon atoms.

35

12. A polythiophene-based conductive polymer liquid composition as set forth in claim 7, wherein the amide solvent is selected from the group consisting of formamide, N-methylformamide, N,N-dimethylacetamide, N-methylpropionamide, N-methylpyrrolidone, and mixtures thereof.

40

13. A polythiophene-based conductive polymer liquid composition as set forth in claim 7, wherein the sulfonic acid group-containing monomer dopant is selected from the group consisting of p-toluene sulfonic acid, dodecylbenzene sulfonic acid, 1,5-anthraquinonedisulfonic acid, anthraquinonesulfonic acid, 4-hydroxybenzene sulfonic acid, methylsulfonic acid and nitrobenzene sulfonic acid.

45

50

55

**EP 0 999 242 A1**



EP 0 999 242 A1



European Patent  
Office

EUROPEAN SEARCH REPORT

Application Number  
EP 99 12 1646

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 825 219 A (BAYER AG) 25 February 1998 (1998-02-25) * the whole document *	1-13	C09D5/24 C08G61/12
A	US 5 773 150 A (HU CHUN-MIN ET AL) 30 June 1998 (1998-06-30) * the whole document *	1,7	
A	DE 196 50 147 A (BAYER AG) 10 June 1998 (1998-06-10) * the whole document *	1,7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09D C08G H01B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 8 February 2000	Examiner MILLER, A
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P/AC01)

# EP 0 999 242 A1

## ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 99 12 1646

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-02-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0825219 A	25-02-1998	DE 19633311 A CN 1175610 A JP 10088030 A	26-02-1998 11-03-1998 07-04-1998
US 5773150 A	30-06-1998	NONE	
DE 19650147 A	10-06-1998	AU 5751098 A WO 9825274 A	29-06-1998 11-06-1998

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82